

A Concise Guide on Textile Dyes, Pigments and Dye Intermediates with Textile Printing Technology

Author: Dr. H. Panda

Format: paperback

Code: NI249

Pages: 512

Price: Rs 1675 | US\$ 150

Publisher: NIIR PROJECT CONSULTANCY SERVICES

Shipping: 5 days

About the Book

In the past, only organic matter was available for making dyes. Today, there are numerous options and methods for the colorization of textiles. While today's methods capitalize on efficiency, there is question as to whether the use of chemicals is harmful to the environment. A reputation for harming the earth could be detrimental to a company in a society becoming more and more focused on the environment and its preservation. Today, with the invention of synthetic materials used in textiles, many new types of dyes have been developed and put into regular use. There are two basic ways to color textiles: dyes and pigments. Pigments are not a dye but rather resins mechanically bound to fibers. Dyes are divided into classes according to the types of fibers they are most compatible with. Textile printing is related to dyeing but, whereas in dyeing proper the whole fabric is uniformly covered with one color, in printing one or more colors are applied to it in certain parts only, and in sharply defined patterns. Dyes will yield the softest hand (the "hand" is the feel of the fabric) and maintain the fabric's luster but the process is expensive. Pigments are much more economical to use. Pigments are generally more lightfast, more colorfast, and give greater color control. Pigment technology has developed tremendously in the past 15 years. 85% of the textile printing in the World is pigment printing. This book contains manufacturing process and other related details about Azine dyes, Azoic dyes, Azo dyes, Thiazole dyes, Triphenylmethane dyes, scientific classification of Vat dyes, fluorination of dyes, different types of pigments, applications, usages of dyes and pigments, quality control and evaluation of pigments and many more. This book will serve as a guide to Textile Technologists, Scientists and existing as well as upcoming industries.

Contents

1. AZINE AND RELATED DYES

Methods of Manufacture

Oxazines

Dioxazines

Thiazines

Commercial Grades and Specifications

Methods of Analysis

Identification

Determination of Specific Structure

Assay Methods

Spectrophotometric Methods

Titration Methods

Miscellaneous Assay Methods

Application Methods

Application to Wool

Application to Cotton

Application to Paper

Application to Leather

Determination of Impurities

2. AZOIC DYES

Azo Coupling Components

Bases

Rapid Fast Colours

Rapidogens

Manufacturing Process

m-Nitro Aniline (Fast orange R)

Properties

Solubility

O-chloroaniline (Fast Yellow G, GC)

Properties of O-Chloroaniline

O-Anisidine (Fast Red BB)

Reduction

Properties

Nitro-p-anisidine (Fast Bordeaux GP)

Purification

Nitration

Hydrolysis

Purification

Naphthol AS-OL

Physical Properties of Naphthol AS-OL

Naphthol AS G

Raw materials

3. AZO DYES

Methods of Manufacture

Methods of Analysis

Identification

Hydrolysis

Nitric Acid Split

Identification of Arylamines in Cleavage Products

Identification of Diamines in Cleavage Products

Identification of Coupling Components

Separation

Blowout Method

Adsorption Chromatography

Application Method

Assay Methods

Salt Test

Titanous Chloride Reduction

Absorption Spectrophotometry

4. THIAZOLE DYES

Direct Dyes, 918

Disperse Dyes, 924

Direct Dyes

Basic Dyes

Vat Anthraquinone Dyes
Health and Safety Factors
Disperse Dyes
Preparation of a Disperse Azo Dye
Cationic Dyes
Health and Safety Aspects
5. INDIGOSOL
Uses of Solubilised Vat Dyes
Manufacture Process Anthrasol Brilliant
Orange Irc (Leuco Sulphuric Ester of
Dibromoanthanthrone)
Test
Anthrasol Blue IBC
Oxidation to Tetraester
General Observations
Identification of Leuco Ester Vat Dyes
6. INDIGOID DYES
Methods of Manufacture
Commercial Grades and Specifications
Methods of Analysis
Identification
Classification of Dye Samples
Procedure
Classification of Dyes on Fiber's
Procedure
Identification of Individual Dyes
Spectrophotometric Identification
Separation
Column Chromatography
Paper Chromatography
Assay Methods
Vatting Method
Methanol-Hydrochloric Acid Method
Spectrophotometric Method
Titration Methods
Elemental Analysis
Halogens
Sulfur
Nitrogen
Determination of Impurities and Additives
Application Methods
7. REACTIVE DYES
History
Developments
Dyes can attach themselves to the fibre in three ways
8. TRIPHENYLMETHANE AND RELATED DYES
Methods of Manufacture
Aldehyde Method
Ketone Method
Hydrol Synthesis
Diphenylmethane Base Method

Methods of Analysis

Identification

Blowout Method

Capillary Test

Dyeing Test

Procedures

Assay Methods

Cerimetric Titration

Titanous Chloride Titration

Spectroscopic Methods

Purification of Standards

9. SCIENTIFIC CLASSIFICATION OF VAT DYES

Five Membered Rings

Two Heteroatoms

Attachment at 2-position

Attachment at 1,2-position

Attachment at 2,3-position

Attachment at 1,9-positions

Vat Dyes Containing Six Membered Rings

One Heteroatom

Attachment at 1, 9-positions

Attachment at 3,4-position of benzanthrone

Six Membered Rings Containing more than one

Heteroatom (from Anthraquinone)

Attachment at 1-position

Attachment at 1,2-positions

Attachment at 2,3-position

Attachment at 1,9-position

Fused Ring System

Dyes containing larger ring systems

10. FLUORINATION OF DYES

Hydrofluoric Acid

Materials of Construction

Fluorine

Material of Constructions

Indanthrene Brilliant Violet F3RK (C.I. 63350)

Indanthrene Blue CLB

Indanthrene printing blue HFG

Nuclear Fluorination

11. PIGMENTS

Chemical Analysis

General methods

Ash and Moisture Content

Alkalinity, Acidity, and pH

Material Soluble in Water

Presence of Organic Colours and Lakes

Pigment Content of Paste in Oil

Testing of Specific Inorganic Pigments

Titanium Dioxide Composites

Carbonate White Lead

Sulfate White Lead



Silicate White Lead
Zinc Oxide
Leaded Zinc Oxide
Zinc Sulfide
Lithopone
Antimony Oxide
Extenders
Calcium Carbonate
Calcium Sulfate
Magnesium Silicate
China Clays
Mica
Other Natural Silicates
Silica
Magnesium Carbonate And Magnesium Oxide
Barium Sulfate
Red, Maroon, And Brown Pigments
Iron and Manganese Oxide Pigments
Van Dyke Brown
Cadmium Mercury Reds
Copper Reds
Red Lead
Mercuric Oxide
Yellow and Orange Pigments
Iron Oxides
Chromate Pigments
Strontium Chromate
Green Pigments
Chrome Greens
Chromium Oxides
Blue and Purple Pigments
Iron Blues
Ultramarine Blues
Blue Lead
Cobalt Blues
Black Pigments
Carbon Black
Iron Oxide Blacks
Metallic Powders
Lead Powder
Zinc Powder
Testing of Specific Organic Pigments
Physical Testing of Properties
Colour
Tinting Strength
Opacity
Particle Size
Testing for Coarse Particles
Fine Particle Distribution
Oil Absorption
Dispersibility, Texture, and Rheology

Solubility
Density
Stability and Fastness
Other Properties
Perylene and Quinacridone Reds
Perylene Red Pigments
Preparation
General Properties
Perylene (Vermilian)
Pigment Red BL
Perylene Red
Perylene Maroon
Perylene Scarlet
Perylene Red Y
Quinacridone Red Pigments
General Properties
Rodamine Y (Pink toner)
Preparation
Properties of various red pigments compared:
Monazo Pigments
Naphthol red pigments
Precipitated (metalized azos) pigments
Non azo pigments
Pigment Orange-2 (Mono Azo Orthonitro Aniline Orange)
Pigment Orange-S (Mono Azo Dinitroaniline Orange)
Pigment Orange-13 (Pyrazolone Orange)
Pigment Orange - 16 (Dianisidine Orange)
Pigment Orange 17: 1 (Persian Orange Lake)
Pigment Orange-34 (Diarylide Orange, Disazo Pyrazolone)
Pigment Orange-36 (Benzimidazolone Orange
HL, Monoazo Acetoacetyl Type)
Pigment Orange-38 (Naphthol Orange)
Pigment Orange-43 (Perinone Orange)
Pigment Orange-46 (Ethyl red Lake C)
Pigment orange 48 and pigment orange 49
(Quinacridone gold and quinacridone deep gold)
Pigment : Orange 51 (Pyranthrone Orange)
Organic Yellow Pigments
C.I. Pigment Yellow 1
C.I. Pigment Yellow 3
C.I. Pigment Yellow 3
Cl. Pigment Yellow 65 (Arylide Yellow RN)
Pigment yellow 74 is an isomer of P. Y .65 and
possesses identical characteristics
C.I. Pigment Yellow 98
Diarylides
C.I. Pigment Yellow 12
Cl. Pigment Yellow 13
C.I. Pigment Yellow 14
Cl. Pigment Yellow 17 (Diarylide Yellow AAOA)
Cl. Pigment Yellow 81 (Diarylide Yellow H10 G)

Heterocyclic yellow organic pigments

Cl. Pigment Yellow 24 (Flavanthrone Yellow)

Cl. Pigment Yellow 60 (Arylide Yellow 4R)

C.I. Pigment Yellow 100 (FD & C Yellow No. 5)

C.I. Pigment Yellow 104 (FD & C Yellow No. 6)

Organic Green Pigments

C.I. Pigment Green

C.I. Pigment Green 4r (Melachite Green PTMA)

Copper phthalocyanine green

C.I. Pigment Green 10 (Nickel Azo Yellow: Green Gold)

12. INTERMEDIATES FOR DYES AND PIGMENTS

Electrophilic

Free Radical

13. APPLICATION, USAGES OF DYES AND PIGMENTS ON TEXTILES

Introduction

Colour Index

Preparation of The Textile Material Prior to

Colouration

Dyeing of Textiles

Substantive or Direct Dyes

(a) Cationic Dye-fixing agents:

(b) Copper Sulphate + Sodium or Potassium

Dichromate + Acetic Acid:

(c) Chromium Fluoride or Acetate + Acetic Acid :

(d) Formaldehyde:

(e) Diazotization and Development:

(f) Coupling with diazotized Fast Bases:

(g) Topping with Basic Dyes:

(h) Back-tanning of Nylon-dyed with Direct Dyes:

S.D.C. Classification of Direct Dyes with regard to levelling properties

Basic and Modified Basic Dyes

Acid and Metal Complex Dyes of the

Acid Class

Details of Dyeing

Other Usages

Cellulose Diacetate

Bast Fibres

Paper

Leather

Miscellaneous Uses

Chrome and other Mordant Dyes

Chrome Dyes

Reactive Dyes

Dissolving of Reactive Dyes

Dyeing of Cotton

Other Uses of Reactive Dyes

Wool Dyeing

Silk Dyeing

Nylon Dyeing

Reactive Disperse Class
Dyeing Procedure
Reactive Wool Dyes
Dyeing Procedure
Azoic or Insoluble Azo Dyes
Dyeing Procedure
Impregnation in Naphthol
Developing Bath
Aftertreatment
Note
Popular Azoic Combinations
New Developments in Azoic range by Hoechst
Specialized application for dyeing of Warp yarn applied
during sizing for Cotton Denim, Jean etc.
Procedure
Azoic Dyestuffs on other Textile Fibres
Sulphur Dyes
Application
Standing Bath
Aftertreatment
Recent Developments
Vat, Solubilized Vat and Sulphurized Vat Dyes
Vat Dyes
Indigoid Vat dyes
Dyeing by Pigmentation procedures
Pigment Padding
Pad-steam-continuous Dyeing process
Wet-on Dry process
Wet-on Wet Process
The Standfast Molten Metal Dyeing Process
Dyeing a Elevated Temperature
Vat Acid Leuco Method
Dyeing of Vat dyes on Pure Silk
Dyeing of Vat dyes on Wool
Dyeing of Synthetics
Dyeing of Bast Fibres
Other Uses
Dyeing of Indigo
Indigo for Cotton Denims
Wool
Sulphurized Vat Dyes
Dyeing Procedure
Solubilized Vat Dyes
Application
All-jig Process
Pad-jig Process
Aftertreatment
Continuous Dyeing Process
Dyeing of other materials
Disperse Dyes
Classification of the various Disperse Dyes according to their



Dyeing characteristics:

Rapid Dyeing Dyes

Dyeing of Disperse Dyes on Polyester

Dyeing Methods

Dyeing of Blends of Polyester with other fibres

Dyeing of Disperse Dyes on other fibres and Miscellaneous applications

Colouring of Smoke Clouds

Pigments (Emulsion Composition & Dry Powder)

Application

Printing of Cotton

Sequence

Dyeing of Cotton Piece Goods with Pigment emulsion

Daylight Fluorescent Pigments for Printing

Ingrain Dyes

Dyeing with C.I. Ingrain Blues 2 on Cotton

Typical examples of Dyeing Procedures

Dyeing of C.I. Ingrain Blue 1 on Cotton

(Alcian Blue 8GX - 300 (I.C.I.))

Solvent Dyes & Food Colours

Oxidation Bases

Dyeing of Aniline Black

Cotton yarn by one-bath process

Oxidation Aniline Black (also called Aged Aniline Black)

Other uses of Oxidation Bases

Mineral Khaki (Inorganic Colourant)

Sequence

Dark Olive Green/Scamic green shade for certain categories of Cotton material for Defence services (India)

Topping with Mineral Khaki on pre-dyed material with Vat dyes

Fluorescent Brighteners

Natural Dyes (C.I. Natural Colour Class)

Useful Information in Dyeing & Printing

(i) Liquor-to-goods ratio or Material-liquor ratio denoted as "M.L.R."

(ii) Depth of Shade in Dyeing

(iii) Padding

(iv) Depth of Shades in Printing

Printing of Textiles

Styles in Printing

They are:

Direct Printing Styles on Cellulosics

Printing with Reactive Dyes

Printing with Pigment Printing Compositions

Printing with Azoics

Naphthol-Nitrite Padding process

Printing with "Rapid Fast" (Hoechst) Dyes

Printing with "Rapidogen" (Bayer) Dyes

Non-acid Steam Process for Rapidogens

Printing with Vat dyes

Typical Recipes

Flash-ageing method

Printing with Solubilized Vat Dyes

Non-steaming Method

Steaming Method using Ammonium Sulphocyanide

Printing Sequence

Printing with Ingrain Dyes

(a) Printing with Alcian - 'X' (ICI) dyes

(b) Printing with Phthalogen Brilliant Blue IF-3G (Bayer)

Printing with Aniline Black

(Oxidation Base Class)

Typical recipes

Printing with Alizarine Red (Mordant Class)

Typical recipes

Printing with Direct Dyes

Typical recipe for printing of Directs

Basic Dyes

Direct Printing of Selected Dyes of

Different Classes Alongside or

Admixed with each other

Typical recipes (Block Prints)

Direct Printing Style on Pure Silk

Typical recipes

Direct Printing Style on Wool

Typical recipes

(i) Reactive Dyes (All types)

(ii) Acid Dyes

(iii) Chrome Dyes

(iv) Metal-complex Dyes (11) particularly Black

Printing of Tufted Carpets

"Vigoureux" or "Melange" Printing

Typical recipes

With Acid Milling and 2:1 Metal-Complex Dyes

Direct Printing Style on Nylon

Typical recipes

Pigment Emulsions

Direct Printing Styles on Polyester,

Triacetate and Diacetate with Disperse

Dyes

Process after Printing

"Melange (Vigoureux)" Printing of Polyester Sliver

Cellulose Triacetate

Cellulose Diacetate

Direct Printing Styles on Acrylics

Sequence

Direct Printing Styles on Fabric

From Fibre Blends

(i) Polyester/Cellulose

(ii) Polyester/Wool

(iii) Cellulosic fibre/Wool

(iv) Cellulosic fibre/Silk



(v) Wool/Silk
 (vi) Cellulosic fibre/Diacetate
 (vii) Cotton viscose or Polynosic fibre etc
 Resist Printing Style on Cellulosics
 Resists under Naphthols
 Resists Under Vat
 Typical recipes
 Resists under Solubilized Vats
 Rapldogen Resists
 Rapid Fast Resists
 Resists under Reactives
 Reactive Dyes Resists under Reactive dyes using
 Remazol-type Dyes for the 'Ground' shade and
 Proclon-type Dyes as 'Illuminants'
 Resists under Aniline Black
 White Resist
 Coloured Resists under Aniline Black
 Basic Colour Resists
 Resists under Phthalogen Brill Blue IF3G (Bayer) ground
 Resists under Basic dyes
 Resists under Acid Milling dyes and 2 1 Metal Complex dyes
 dyed on Pure Silk
 Discharge Printing Style
 (a) White discharge
 (b) Colour discharge
 Discharge Printing on Dyed Cellulosics
 (a) On Direct dyes dyed ground
 (b) Discharge Printing on Naphthol Dyed Ground
 (c) Discharge printing on Reactive dyes dyed ground
 Discharge Printing of Dyed Natural Silk
 Based on Sodium, Sulphoxylate Formaldehyde (Rongolite C)
 Based on Sodium-Bisulfate + Zinc Dust
 Illuminant Dyes (for Colour discharge)
 Discharge Printing of Dyed Wool
 With Acid/Direct dyes
 Discharge Printing of Polyester Dyed with
 Disperse Dyes
 Ground shades for Discharge printing
 Pre-dyeing by pad method
 Pre-dyeing by H.T. process
 Pre-printing
 Typical examples for Discharge printing
 Procedures for Discharge Printing of Polyester dyed
 by H.T. dyeing
 Discharge Printing of Dyed Cellulose DI & TRI
 Acetate and Nylon
 Typical Recipes
 White Discharge on Cellulose Diacetate and Nylon dyed
 with Disperse dyes
 Colour Discharge of Nylon dyed with Disperse Dyes
 Discharge Printing of Nylon dyed with suitable dischargeable

Acid, Metal-complex and some limited Direct Dyes
Miscellaneous Applications in Dyeing
and Printing
Transfer printing
Mechanical Resist Colouration
Resist Printing of Vinyl Sulphone type Reactive Dyes by
“Blocking” Chemically the Reactive group
“Khadi” Printing
Conversion Style of Printing
Novel graded-shade effect on Cotton yarn by “Dyeing
Polychromatic Dyeing
Speckle Printing
Burn-out Styles
After treatment
14. COLOURANTS FOR DRUG
15. QUALITY CONTROL AND EVALUATION OF
PIGMENTS
Quality Control
Evaluation of Pigments
Physical Properties of Pigment
Moisture Content
Procedure
Bulking Volume
Procedure
Mesh Residue
Particle Size
Solvent Stability
Aim
Importance of the test
IS Value
pH of the Pigment
Oil Absorption
Raw Materials Required
Defination of Oil Absorption
Opacity
Colour
Reduction Tone
Raw Materials Used
Other materials required
By Automatic Muller
Mass Tone
Apparatus required
Raw Material required
Dispersibility, Texture, and Rheology
Stability and Fastness
Other properties
To determine the sp. Gravity of Pigment
Method
Volumetric Method for the determination of
Copper in Cuprous Chloride
Estimation of Organically Bound Chlorine

Calculation

The Infra-Red Identification of Pigments

NIIR PROJECT CONSULTANCY SERVICES (NPCS) is a reliable name in the industrial world for offering integrated technical consultancy services. NPCS is manned by engineers, planners, specialists, financial experts, economic analysts and design specialists with extensive experience in the related industries.

Our various services are: Detailed Project Report, Business Plan for Manufacturing Plant, Start-up Ideas, Business Ideas for Entrepreneurs, Market Research, Manufacturing Process, Machinery, Raw Materials, Project Feasibility, Investment Opportunities, Technical Consultancy and Startup Help.

NPCS also publishes process technology books, technical books, startup books, directory, business database, detailed project reports and market research reports.

Our Detailed Project Report aims at providing all the critical data required by entrepreneurs for starting new business ventures.

NIIR PROJECT CONSULTANCY SERVICES

106-E, Kamla Nagar, New Delhi-110007, India

Email: npcs.india@gmail.com **Website:** <https://www.niir.org/>